

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (currently amended): A ~~film-like materials of resin manufacturing~~ method for producing a film-like material made of a resin by rolling a thermoplastic resin material containing a thermoplastic resin using a molding apparatus comprising first rotation molding members composed of a pair of rollers, characterized in that the rolling is carried out under the condition 1 that the line contact pressure P (kN/m) applied to the thermoplastic resin, the peripheral velocity R (m/sec) of the rollers of the first rotation molding members, and the thickness H (m) of the film-like material made of the resin after rolling satisfy the following inequalities:

(formula 1) $3 \times 9.8 \leq P$

(formula 2) $3 \times 9.8 \times 10^{-6} \leq P/(R/H^2) \leq 2 \times 9.8 \times 10^{-5}$.

2. (canceled).

3. (currently amended): The ~~film-like material of resin manufacturing~~ method for producing a film-like material made of a resin as claimed in claim 1, characterized in that the rolling and molding is carried out while setting the surface temperature T of said first rotation

molding members to be employed for the rolling and molding so as to satisfy the following conditions defined as (formula 3) or (formula 4):

in the case the thermoplastic resin is crystalline,

(formula 3) $T > T_m$ and

in the case the thermoplastic resin is not crystalline,

(formula 4) $T > T_g$, wherein the reference character T_m is the melting point of the crystalline thermoplastic resin and the reference character T_g is the glass transition temperature of the not crystalline thermoplastic resin.

4. (currently amended): ~~A film-like materials of resin manufacturing method~~ for producing a film-like material made of a resin by rolling a thermoplastic resin material containing a thermoplastic resin using a molding apparatus comprising first rotation molding members composed of a pair of rollers, characterized in that the rolling is carried out while setting the surface temperature T of said first rotation molding members so as to satisfy the following condition 1 and condition 2:

<condition 1>

at the temperature T , the melt tensile strength MT (g) and the drawing degree L of the thermoplastic resin fulfill the following ranges

(formula) $MT > 10 \text{ g}$ and $L > 100\%$.

<condition 2>

in the case the thermoplastic resin is crystalline,

(formula 3) $T > T_m$ and

in the case the thermoplastic resin is not crystalline,

(formula 4) $T > T_g$, wherein the reference character T_m is the melting point of the crystalline thermoplastic resin and the reference character T_g is the glass transition temperature of the not-crystalline thermoplastic resin.

5. (currently amended): The ~~film-like materials of resin manufacturing method~~ as claimed in any one of claims 1, 3 and ~~to~~ 4, wherein the peripheral velocities of the pair of the rollers composing said first rotation molding members are approximately equal speed.

6. (currently amended): The ~~film-like materials of resin manufacturing method~~ as claimed in claim 4, wherein the film-like materials of resin produced by rolling and molding by said first rotation molding members is successively brought into contact with second rotation molding members composed of rollers rotating at a peripheral velocity at least 1.08 times as fast as the peripheral velocities of the first rotation molding members.

7. (currently amended): The ~~film-like materials of resin manufacturing method~~ as claimed in claim 4, wherein said thermoplastic resin contains 10 wt % or more of a thermoplastic resin having a molecular chain length of 2850 nm.

8. (currently amended): The ~~film-like materials of resin manufacturing method~~ as claimed in claim 4, wherein said thermoplastic resin contains 10 to 300 parts by weight of a filler to 100 parts by weight of the thermoplastic resin.

9. (currently amended): A crystalline thermoplastic resin film characterized in that the film contains 10 to 300 parts by weight of a filler to 100 parts by weight of the crystalline thermoplastic resin and ~~in that~~ the orientation coefficient of the c-axis of the crystal in said film to the MD direction of said film is 0.8 or higher.

10. (original): The crystalline thermoplastic resin film as claimed in claim 9, characterized in that said crystalline thermoplastic resin is a polyolefin-based resin.

11. (original): The crystalline thermoplastic resin film as claimed in claim 10, characterized in that said polyolefin-based resin contains 10 wt % or more of polyolefin with a molecular chain length of 2850 nm or longer.

12. (canceled).

13. (currently amended): A crystalline thermoplastic resin film manufacturing method comprising a rolling step for rolling a crystalline thermoplastic resin using at least one pair of rolls to obtain a film having 0.8 or higher orientation coefficient of the c-axis of the crystal in

said film to the MD direction of said film, wherein the surface temperature T of the rolls in said rolling step and the melting point T_m of the crystalline thermoplastic resin satisfy the following (formula 6):

(formula 6): $T > T_m$.

14. (canceled).

15. (currently amended): The crystalline thermoplastic resin film manufacturing method as claimed in claim ~~14~~ 13, characterized in that the surface temperature T of the rolls in said rolling step is the temperature at which the melt tensile strength MT and the drawing degree L of said crystalline thermoplastic resin fulfill the following ranges:

(formula) $MT > 98 \text{ mN (10 gf)}$ and $L > 100\%$.

16. (original): The crystalline thermoplastic resin film manufacturing method as claimed in claim 15, characterized in that said crystalline thermoplastic resin is a polyolefin-based resin.

17. (original): The crystalline thermoplastic resin film manufacturing method as claimed in claim 16, characterized in that said crystalline thermoplastic resin contains 10 to 300 parts by weight of a filler to 100 parts by weight of said resin.